

Strong Mountain METAL

1775 Old Gray Station Road
 PO Box 3269
 Johnson City, TN 37615
 (423) 282-0844 main
 (800) 936-0844 toll free
 (423) 282-3020 fax



Charcoal Gray
 SR .27 SRI 26



Desert Sand
 SR .42 SRI 47



Burnished Slate
 SR .28 SRI 27



Cocoa Brown
 SR .30 SRI 27



Ivy Green
 SR .28 SRI 27



Rustic Red
 SR .36 SRI 38



Hawaiian Blue
 SR .32 SRI 32



Black
 SR .30 SRI 30



Ash Gray
 SR .47 SRJ 55




Saddle Tan
 SR .48 SRI 55



Berry
 SR .30 SRI 27



Light Stone
 SR .50 SRI 57



Polar White
 SR .60 SRI 71

- Final color selection should be made from actual color chips.
- A 40-year limited paint warranty is available for all colors upon written request. (Outside the continental United States, please inquire.)
- Solar reflectivity (SR): Solar reflectivity or reflectance is the measure of a material's ability to reflect solar energy from its surface. SR values are numbered 0 to 1.0. A value of 0 indicates that the surface absorbs all solar energy and a value of 1.0 indicates total reflectance. ENERGY STAR requires an SR of 0.25 or higher for steep slope roofing (above 2:12) and an SR value of 0.65 or higher for low slope roofing (2:12 or less).
- Solar Reflectance Index (SRI): The SRI is used to determine compliance with LEED requirements and is calculated according to ASTM E 1980 using values for reflectance and emissivity. To meet LEED material requirements, a roofing material must have an SRI of 29 or greater for steep slope roofing and an SRI value of 78 or higher for low slope roofing.

**Available in
 29 GA only.**

valspar[®]

